



Eppco Enterprises, Inc.
544 S. Green Rd.
Cleveland, OH 44121
(216)382-8300
sales@eppco.net

Product Specifications - NitrilePlus 8-mil Gloves

1.0 Product: Nitrile, Pre-powdered/ Powder Free, textured, 12” length, for examination use

2.0 Physical Dimensions:

Size	Length (mm) (min)	Width (mm)	Thickness (mm)	
			Palm	Finger
S	290	80 ± 10	0.20 ± 0.03	0.24 ± 0.03
M	290	95 ± 10	0.20 ± 0.03	0.24 ± 0.03
L	290	110 ± 10	0.20 ± 0.03	0.24 ± 0.03
XL	290	120 ± 10	0.20 ± 0.03	0.24 ± 0.03

3.0 Physical Requirements :

Before Aging:

Tensile Strength: 14 MPA (min); Elongation: 500% (min)

After Accelerated Aging:

Tensile Strength: 14 MPA (min); Elongation: 400% (min)

4.0 Freedom from holes: According to ISO 2859, G-II, multiple sampling plan for normal inspection, AQL 1.5

5.0 Powder Residues: For Pre-powdered gloves, not more than 10mg/dm²; for powder free gloves, not more than 2mg per glove.